

O'zbekiston

Kompozitsion **M**ateriallar

Ilmiy-texnikaviy va amaliy jurnali



Узбекский научно-технический и производственный журнал
Композиционные материалы

Работа выполнена в рамках совместного Узбекско-Белорусского фундаментального проекта IL-4821091571 “Новые методы получения гибридных полимерных суперабсорбентов на основе полисахаридов и полиакрилатов”.

ЛИТЕРАТУРА:

1. Ahmed Enas M. // J. Adv. Res. 2015. V. 6. № 2. -P. 105.
2. Liu Y., Wang J., Chen H., Cheng D. // Sci. Total Environ. 2022. Nov 10. 846:157303.
3. Sikder A., Pearce A.K., Parkinson S.J., Napier R., O'Reilly R.K. // ACS Appl. Polym. Mater. 2021. V. 3. № 3. -P. 1203.
4. Rather R.A., Bhat M.A., Shalla A.H. // Carbohydr. Polym. Technol. Appl. 2022. V. 3. -P. 100202.
5. Chen J., Wu J., Raffa P., Picchioni F., Koning C.E. // Prog. Polym. Sci. 2022. V. 125. -P. 101475.
6. Bhavsar C., Momin M., Gharat S., Omri A. // Expert Opin. Drug Delivery. 2017. V. 14. № 10. -P. 1189.
7. Kudyshkin V.O., Abrarova Z.M., Bozorov N.I., Zhumartova U.U., Usmanova M.M., Ashurov N.Sh, and Rashidova S.Sh. // Polymer Science, Series B, 2024, Vol. 66, No. 1, -Pp. 51–58. DOI: 10.1134/S1560090424600165
8. Mochalova A.E., Zaborshchikova N.V., Knyazev A.A., Smirnova L.A., Izvozchikova V.A., Medvedeva V.V., Semchikov Yu.D. // Polymer Science A. 2006. V. 48. № 9. -P. 918.

ENHANCING THE STRENGTH OF ASPHALT CONCRETE THROUGH RHEOLOGICAL PROPERTIES

Abdurazakov Mirzohid

Namangan engineering-construction institute

Abstract: This article is devoted to the improvement of the rheological properties of asphalt concrete and its strength based on the addition of surfactants, secondary industrial waste and polymers. Additives used to increase the strength of asphalt concrete through the rheological properties of bitumen or asphalt concrete mixture, surfactants and polymers, were carried out in laboratory conditions and the results of the research are presented.

Keywords: Bitumen, asphalt concrete, surfactants, secondary industrial waste, polymers, production technologies, testing, physical and mechanical parameters, sample testing methods, etc.

Asphalt-concrete pavements make up the majority of public highways in Uzbekistan. Ensuring the service life and durability of asphalt concrete pavements is one of the main problems.

In order to prevent such situations, it is necessary to carry out research on the quality indicators of asphalt concrete with additional surfactants, secondary industrial waste, polymers and their mixtures. It is planned to increase the durability of asphalt concrete in two ways:

- addition of surface-active substances to improve the physical and mechanical properties of bitumen added to asphalt concrete;

- adding surfactants to the asphalt concrete mixture.

To do this, we select the following additional substances:

Alfadob, "Honeywell 7686", "Titan 7686", mixture of crushed rubber powder with polymer, Topcell, Ekotop and Chrysopro were studied.

Alfadob, "Honeywell 7686" and "Titan 7686" are added to improve the physical and mechanical properties of bitumen.

The tolerance of the rheological properties of asphalt concrete is increased by mixing crushed rubber powder with polymer, and adding Topcell,

Ekotop, and Chrysopro to the asphalt concrete mixture as a surface-active substance.

Alfadob is a liquid surface-active bituminous additive for improving the adhesion of bitumen to stone material based on organic ethers and industrial waste vegetable oils. Alfadob is added to the asphalt-concrete mixture in the proportion of 0.1-0.3% compared to bitumen. Alfadob provides extreme thermal stability (2-3 weeks in hot bitumen) and improves water absorption and crack resistance properties of the pavement surface [2].

Alfadob retains its quality indicators regardless of the physical and mechanical characteristics of the stone material. It creates a strong hydrogen bond between the bitumen and the limestone and provides perfect adhesion. It works not only with acid rocks (e.g. quartz, granite, porphyry, etc. / basic silicates), which form negatively charged SiO₃²⁻ ions along with the moisture that is always present on their surface, but also with all the main types of rocks (e.g. dolomite, limestone, etc.) gives good results when used [3].

One of the multifunctional road construction composite materials made from polymer waste used in industry is the polymer "Honeywell 7686" containing polyethylene, titanium and wax.

Honeywel specification 7686 is a low molecular weight, multi-functional, polyethylene-based wax optimized for effective bitumen modification. The viscosity of the polymer solution is very low. Therefore, the use of the surfactant "Titan 7686" allows manufacturers to significantly increase adhesion and save polymer.

It ensures compliance with "GOST-9128-2013", increases cold resistance, improves elasticity, reduces the occurrence of cracks, enhances water resistance. By using a simple blending agent, the polymer is added to the bitumen and easily melts at 150°C. Additionally, after the asphalt concrete mixture is laid, it reduces the release of carbonate and anhydrite gases under hot climate conditions. It is possible to prepare the asphalt concrete mixture without any additional additives or directly add polymer-bitumen to the bitumen.

Additionally, one of the most common and promising projects in world practice is the enrichment of bitumen composition with

thermoplastics, which combine the properties of thermoplastics and elastomers. By using these thermoplastics, it is possible to improve the quality of bitumen. In order to increase the quality of bitumen, it is advisable to add polymer in the proportion of 2.5-6% of the total mass of bitumen..




Figure 1. The process of pouring bitumen samples enriched with "Honeywell 7686" polymer into molds for testing in the laboratory.

In this case, the quality indicators of asphalt concrete will be improved to some extent. We can see it in the table below [4].

Table 1.

Physico-mechanical properties of "Honeywell 7686" polymer-added asphalt concrete

Name of indicators	Amount
Average density of asphalt concrete, kg/m ³	2360
Water absorption	3,5
Porosity	0,1
Compressive strength at a temperature of 20 °C	3,8
Water resistance coefficient	1,21

In order to increase the durability of asphalt concrete, in order to enrich the bitumen composition with the help of surfactants, taking into account the above actions, we carry out the following works.

For this, the selected bitumen sample is placed in a metal container with a volume of about 10 liters and placed in a thermal cabinet with a thermometer. The bitumen sample is heated to a temperature of 145-155°C, while the temperature should not exceed 160°C. The reason is that overheating of the temperature can change the properties of bitumen and materials added to it. When the bitumen is

heated to the temperature indicated above, it is removed from the heating furnace and poured into the laboratory mixer. In addition, a 13% rubber solution and pre-crushed polyethylene are added in the required amount of gasoline [5]. The mixture is stirred at a temperature of 160-180°C for 1-1.5 hours until all components are completely combined. When the composition becomes homogeneous, it is poured into test molds and tested according to GOST-33137-2014. And the results are compared in Table 2 below.

Table 2

BND 60/90 bitumen from modification previous and keying results

№	Indicators names	Measureme nt unit	In practice results		
			According to GOST	Bitumen real value	Modification when done value
1	Needle sunset depth At 25 °C At 0 °C	0.1 mm	61-90 from 20 less it's not	66.3 27	43 21
2	Softening temperature (people and ball by)	°C	from 47 less it's not	48.4	52.9
3	Elongation at 25 °C At 0 °C	cm	from 55 less it's not	72 3.7	59.4 3.9
4	Mortality temperature	°C	-15	-12.4	-14.6
5	Flash temperature	°C	230	from 230 high	from 230 high
6	Penetration index	-	(-1) to 1	-1	-0.7

In addition, pieces of rubber, which remain the main problem as secondary industrial waste, can be used in road construction. In this case, only pieces of rubber can be added to the mixture after processing with polymer. In this case, pieces of rubber as shown in Figure 4 are prepared and processed with polymer (polybutadiene) under special conditions. And it comes in the following form.

This piece of rubber is mixed with limestone and bitumen at a temperature of 170-180 °C in a special mixer for 40-45 minutes. We will prepare 2 different samples based on the requirements of GOST-9128 for testing in the laboratory. The first sample is ordinary asphalt concrete, and the second is asphalt concrete with polymer-treated rubber particles. In this case, rubber is added in the amount of 12.5% of total bitumen and the following content is selected for sample preparation. In addition, asphalt concrete samples enriched with surfactants such as Topcell, Ekotop, Chrysopro are prepared.

Based on the selected composition, samples are prepared for testing in the laboratory and the tolerance of its rheological properties is checked. In this case, its resistance to displacement is tested as follows. In this process, a sample in a water bath at a temperature of 50 °C, a test stamp of a universal press is made in a transverse view, and research is carried out according to the Marshall scheme. [6].




Figure 5. The process of checking the compressive strength of an asphalt concrete sample in a universal press: 1-hinge, 2-cylinder surface, 3-place for sample, 4-bottom plate.

In this process, the tension is checked by applying a tension of 20 (50)KN at a speed of 50 mm/min [7].

Then the following accounting work is done [7].

$$A = \frac{Pl}{2} \quad (1)$$

A- Marshall unit for compression [Joule]

P-supplied voltage

l-test sample size in compression [mm]

Then the coefficient of internal friction of asphalt concrete $\tan \varphi$ is calculated according to the formula [7].

$$\tan \varphi = \frac{3(A_m - A_c)}{3A_m - 2A_c} \quad (2)$$

A_m , A_c , - the average work of deformation of asphalt concrete tone samples when tested according to the Marshall scheme and uniaxial compression

After calculating these, we calculate the shear strength [7].

$$C_l = \frac{1}{2} (3 - 2 \tan \varphi) R_c \quad (3)$$

R_c - sample compression limit [15 MPa].

After completing the above work, we compare according to GOST-9128-2013, GOST-31015 [6-7-8]. And we come to the following result [9-10]:

On the basis of the results of research conducted in laboratory conditions, based on the data presented in the tables, we can conclude as follows:

1. In order to increase the strength of asphalt concrete by enriching the bitumen composition with various surfactants listed above, it is implemented by increasing its rheological properties.

2. By adding additives prepared by mixing polymers with secondary industrial waste to the asphalt concrete mixture, it is possible to improve its rheological properties and increase its quality indicators and durability.

REFERENCES

1. Raximov Sh.T., Xudoynazarova Q.J., "Kompozitsion materiallarning zamonaviy texnologiyalari". O'q. qo'l-ma, Tosh. 21.
2. Maxkamov, D. I., Xabibullayev, A. X., Abdurazaqov, M. A., & Nurxonov, D. X. (2021). Issledovaniye vliyaniya mexanoaktivirovannykh prirodnykh mineralnykh ingrediyehtov na svoystva kompozitsiy dlya asfaltobetonnykh pokrytiy. *Ekonomika i sositum*, (11-2 (90)), 147-153.
3. Maxkamov, Dilshod Ismatillayevich, Inoyatov Qaxramon Muydinovich, and Mirzoxid Abduraxmonxo'jayevich Abdurazaqov. "Issledovaniye sposobov mexanoximicheskoy aktivatsii mineralnykh ingrediyehtov s syelyu polucheniya deformatsionno-sdvigoustoychivyykh asfaltobetonnykh kompozitsiy dlya avtomobilnykh dorog i vybor sposoba i ustroystva ix mexanoaktivatsii." *Universum: texnicheskiye nauki* 11-3 (92) (2021): 16-21.
4. Maxkamov, D. I., et al. "Issledovaniye vliyaniya mexanoaktivirovannykh prirodnykh mineralnykh ingrediyehtov na svoystva kompozitsiy dlya asfaltobetonnykh pokrytiy." *Ekonomika i sositum* 11-2 (90) (2021): 147-153
5. <https://industrial.honeywell.com/us/en/products/performance-additives/asphalt/paving/honeywell-titan-7686>
6. Chechulin D.V. Osnovi texnologii polimernyx kompozitsionnykh materialov na osnove modifitsirovannykh neftyanix bitumov: Diss. kand. texn. nauk - Saratov, 2004. - 135s
7. Kasimov I.I., "Modifikatsiyalangan bitumlar asosidagi asfaltbeton va tom qoplamalarining strukturasi, xossalari va texnologiyasi" Toshkent-2020 Texnika fanlari bo'yicha doktorlik (DSc) dissertatsiyasi 45-71-bet.
8. GOST-12801-98, "Materiali na osnove organicheskix vyajushix dlya dorojnogo i aerodromnogo stroitelstva", metodi ispitaniy. Moskva-1999 Rossiya.
9. GOST 31015-2002 (smesi asfaltobetonnie i asfaltobeton tshbenochno-mastichnie.) Moskva-2003 Rossiya.
10. GOST 9128-2013 - smesi asfaltobetonnie, polimerasfaltobetonnie, asfaltobeton, polimerasfaltbeton. Moskva-2014 Rossiya.

Majidov S.A. Indigoning temir (III), kadmiy (II) va marganes (II) ionlari bilan hosil qilgan komplekslarning haqiqiy molyar so'ndirish koeffitsiyenti va muvozanat konstantasini tolmachyovning grafik usuli bilan aniqlash...	153
Рашидова К.Х., Каттаев Н.Т., Акбаров Х.И., Абдирахмонова Ў., Қаххорова Н. Синтез и исследование электрокатализатора на основе биметаллического фосфида	157
Туробов Ш.Н., Боймуродов Н.А., Хужакулов А.М. Направления переработки вольфрамового сырья в промышленных масштабах	159
Джураев А.Ж. Синтез производных глицирретовой кислоты и их мембранатропные свойства	162
Yusupov A.A., Yo'ldashev X.X. Murakkab shakldagi plastik detallarni ishlab chiqarishda qolipining sovutish samaradorligini oshirish	166
Панжиев А.Х., Зияев Р., Алланов А. Исследование состава полученного цианмида кальция	171
Марданова Ю.У., Камалова Д.И. Исследование колебательного спектра композиционного материала на основе полистирола и сажи (0,03; 0,04)	173
Умурова Ш.Ш., Амонова М.М., Амонов М.Р. Изучение адсорбционные свойства модифицированных бентонитов	175

6. Проблемные обзоры

Хасанова Э.И., Емельянычева Е.А., Башкирцева Н.Ю., Тешабаева Э.У. Современное состояние битумной отрасли Российской Федерации и ассортимент выпускаемых битумных материалов	179
Шодиев А.Н., Каршибоев Ш.Б., Ёрматов Д.А. Аналитический обзор извлечения германия из руд и отходов различных отраслей производства	185
Mardorov U., Xasanov O., Umarov E., Norxo'rozov D. Metallarga mexanik ishlov berishda moylovchi-sovituvchi suyuqliklardan foydalanish texnologiyalari (tahlil)	189
Мухамедбаева З.А., Эшмуратова Р., Алиева Р.А. Влияние вторичных отходов цветной металлургии на свойства цементного клинкера	192
Shonazarova Sh., Sharopova D., Karimov M., Samadov A. Investigation of cobalt recovery from mother liquor	196
Yakubov M.M., Karimova T.P., Maksudxo'jayeva M.S., Yoqubov O.M. Klinkerni kompleks qayta ishlash - rux keklarini quyish chiqindilari	199
Турабов Н.Т., Тоджиев Ж.Н., Тураев Х.Х., Раупова С.С., Усманова М.Д., Сманова З.А. Влияние ионов тяжелых металлов на загрязнение окружающей среды	204
Рахимов Х.Ю., Холматова Н.Г., Билалова Д.Ж. Исследование и разработка состава композиционных эмульгаторов на основе местного сырья и отходов производств и изучение их физико-химических и технологических свойств	207
Негматов С.С., Абед Н.С., Сергиенко В.П., Улмасов Т.У., Бухаров С.Н., Туляганова В.С., Рузиева Б.Ю. Звукопоглощающие композиционные материалы для шумопонижающих конструкций	209
Исроилов О.И., Мухиддинов Б.Ф., Ширинов Ш.Д., Джалилов А.Т. Маҳаллий хомашёлар асосида гидрогеллар синтези ва уларнинг хоссалари	212
Masidikov E.M., Abduraxmonov S.A., Axtamov F.E. Mis boyitish fabrikasi texnogen chiqindilarini qayta ishlasga jalb qilish imkoniyatlari	217
Abdurazakov M. Modern solutions for increasing the strength properties of asphalt concrete pavement	220
Рахимбаев Б.С., Пирматов Е.А., Хасанов А.С. Петрографические исследования руд бакенного рудного поля	224
Sultonov S.B., Kucharov A.A., Yusupov F.M. Nordon gazlardan oltingugurt ajratib olish uchun titan asosli seolit ishlab chiqishning ilmiy asoslari	227
Чулиев У.Х., Амонов М.Р., Шабарова У.Н. Изучение технологических свойств буровых растворов	231
Кудышкин В.О., Абрарова З.М., Бозоров Н.И., Жумартова У.У., Усманова М.М., Рашидова С.Ш. Особенности синтеза привитых сополимеров хитозана и акриламида	234
Abdurazakov M. Enhancing the strength of asphalt concrete through rheological properties	236
Негматов С.С., Исмаилов Р.И., Раупова Д.Н., Рахимов Х.Ю., Мусабеков Д.Х. Исследование жидкой пробы нефтеэмульсии и очищенной нефти с разработанным композиционным деэмульгатором методом ИК-спектроскопии	239
Муфтуллаева М.Б., Реймов М.А. Использование бентонитовых глин приаралья для получения стеновых материалов	242
Абдиназаров А.А., Ёдгоров Н.Н. Разработка состава стабилизированного облегченного тампонажного раствора по внедрению на месторождении алан в скважине №202	245
Губайдуллин Р.Ш., Йўлчиев А.Б., Алимухаммедов М.Г. Изучение физико-механических показателей новых композиций жёстких пенополиуретанов	248
Tashmatov R.K. Matematik modellash tirish asosida yuqori uglerodli po'latlarga termik ishlov berish orqali dislokatsiya zichligining o'zgarishi	251